

LUBA-print 459

TECHNICAL INFORMATION

Chemical description:	Wax dispersion / Wachsdispersion
Application/properties:	Solvent- based lacquers: to improve hydrophoby and antiblocking
Processing information:	3-10 % of this wax dispersion to be added to the lacquer while stirring
Solid:	Paraffine combination
Solvent:	Isoparaffinic Hydrocarbon Boiling Range 153-178°C

Technical data:	Colour	white		
		Minimum	Maximum	Method
	Active content	18,5 %	20,5 %	Sartorius MA 100 infrared drier
	Drop point	97 °C	105 °C	DIN ISO 2176 (solid wax)
	Density	0,76 g/ccm	0,78 g/ccm	Pyknometer DIN EN ISO 2811-1
	Viscosity	8 mPa.s	35 mPa.s	Rheolab MC1 DIN 53019 1.291s-1

These data are also part of the test certificate and the specification.

Storage: In original closed containers lasting at least 12 months at temperatures between 5-35°C. Stir well before use!

Our technical suggestions are based on data from many experiments and cannot represent a warranty of any kind as to their performance in other formulations. Customers must always verify our product's performance in their own systems. This technical data sheet replaces all previous issues.

EN

Revision: 09/2012

MUNZING CHEMIE GmbH

Münzingstrasse 2
74232 Abstatt

Tel.: +49(0)7131/987-0
Fax: +49(0)7131/987-125
lubaprint@munzing.com
www.munzing.com