

LUBA-print 466/F

TECHNICAL INFORMATION

Chemical description:	Wax dispersion / Wachsdispersion
Application/properties:	Aqueous lacquer system with adhesions improvements. To improve antislip.
Processing information:	2 - 10 % of this wax dispersion to be added to the paint while stirring
Solid:	mod. Polypropylene
Emulsifier-system:	non - ionic / anionic
Solvent:	Water
Technical data:	Colour yellowish

	Minimum	Maximum	Method
Active content	38,5 %	41,0 %	Sartorius MA 100 infrared drier
Melting range	118 °C	126 °C	DSC (solid wax) (ISO11357-3)
pH-Value	8,0	9,5	DIN ISO 976
Particle size d98 <=		5,0 µm	Single pass test
Viscosity	90 mPa.s	300 mPa.s	Rheolab MC1 DIN 53019 1.291s-1

These data are also part of the test certificate and the specification.

Storage: In original closed containers lasting at least 12 months at temperatures between 5-35°C. Stir well before use!
Protect from frost! After long storage, particularly after usage of some of the product, evaporation of water is possible and visible signs of particles may be present. We therefore recommend filtration of the product before use.

Our technical suggestions are based on data from many experiments and cannot represent a warranty of any kind as to their performance in other formulations. Customers must always verify our product's performance in their own systems. This technical data sheet replaces all previous issues.

EN

Revision: 02/2015

MÜNZING CHEMIE GmbH

Münzingstrasse 2
74232 Abstatt

Tel.: +49(0)7131/987-0
Fax: +49(0)7131/987-125
lubaprint@munzing.com
www.munzing.com