

LUBA-print 582/E

TECHNICAL INFORMATION

Chemical description: Wax dispersion / Wachsdispersion

Application/properties: Wood-Coatings
to reduce metalmarking.

Processing information: 3 - 10 % of this wax dispersion to be added to the laquer while stirring.
To be added at laquer-processing as soon as possible to ensure an optimal distribution.

Solid: Functional blend

Solvent: Butyl acetate

Technical data: **Colour** white

	Minimum	Maximum	Method
Active content	11,0 %	13,0 %	Sartorius MA 100 infrared drier
Drop point	109 °C	117 °C	DIN ISO 2176 (solid wax)
Density	0,87 g/ccm	0,89 g/ccm	Pyknometer DIN EN ISO 2811-1
Viscosity	2 mPa.s	30 mPa.s	Rheolab MC1 DIN 53019 1.291s-1

These data are also part of the test certificate and the specification.

Additional information: Product can show an increase of viscosity and can build up agglomerates during storage.
Stir well before use!

Storage: In original closed containers lasting at least 12 months at temperatures between 5-35°C. Stir well before use!

Our technical suggestions are based on data from many experiments and cannot represent a warranty of any kind as to their performance in other formulations. Customers must always verify our product's performance in their own systems. This technical data sheet replaces all previous issues.