

# LUBA-print T-152/D30

## TECHNICAL INFORMATION

<b>Chemical description:</b>	Wax dispersion / Wachsdispersion
<b>Application/properties:</b>	Solvent-based paints: to improve slip property and water proofing of wood surfaces. Temporary corrosion protection for metal surfaces.
<b>Processing information:</b>	2 - 6 % of this wax dispersion to be added to the lacquer. For temporary corrosion protection the product is applied undiluted.
<b>Solid:</b>	Functional blend
<b>Solvent:</b>	Dearomatized Hydrocarbon Boiling Range 140-170°C

**Technical data:**                      **Colour**                                      white

	<b>Minimum</b>	<b>Maximum</b>	<b>Method</b>
<b>Active content</b>	18,5 %	21,5 %	Sartorius MA 100 infrared drier
<b>Drop point</b>	98 °C	106 °C	DIN ISO 2176 (solid wax)
<b>Viscosity</b>	thin fluid		

*These data are also part of the test certificate and the specification.*

**Storage:**                                      In original closed containers lasting at least 12 months at temperatures between 5-35°C. Stir well before use!

Our technical suggestions are based on data from many experiments and cannot represent a warranty of any kind as to their performance in other formulations. Customers must always verify our product's performance in their own systems. This technical data sheet replaces all previous issues.