

# AGITAN<sup>®</sup> P 803

## TECHNICAL INFORMATION

### Powder defoamer

<b>Composition:</b>	Blend of liquid hydrocarbons and polyglycols on an inorganic carrier	
<b>Appearance:</b>	powder	
<b>Colour:</b>	white	
<b>Typical Properties:</b>	Ash:	approx. 33 %
	Consistency:	powder
	Apparent density:	approx. 330 g/l
	Solubility in water:	hydrophobic product, dispersible in water

*This information is intended as a guideline only and should not be used to issue specifications. Slight deviations do not affect application and capability of the product. For specifications please consult the Certificate of Analysis.*

**Properties/applications:** AGITAN P 803 is recommended for application in dry blends which are dissolved in water before application. The addition of AGITAN P 803 results in low foaming solutions, specifically aqueous pastes or masses with very low air content. In some mortar systems AGITAN P 803 shows a plastisizing effect, meaning the spreading value is increased. This is ideal for jointless flooring compounds.

**Main applications:**

- Joint fillers and putties
- Leveling compounds
- Screeds (cement and anhydride based)
- Gypsum
- Cement
- Mortars
- Powder paints
- Adhesives

**Recommended levels/use:** Ladder studies are recommended to determine optimum concentration level. Normal dosage ranges from 0.1 to 1 % on finished product. Handling of AGITAN P 803 is convenient with respect to flowability, dusting and ease of incorporation.

**Storage/handling:** AGITAN P 803 is not sensitive to freezing. For better handling it should be stored dry between 15 and 25 °C. The minimum shelf life in closed containers is 15 months from the date of manufacture.

**Packaging:** Pallet with 30 bags, each 15 kg (450 kg)